

6X37 CLASS WIRE ROPE

	Nominal Breaking Strength in Tons of 2000lbs (Bright or Drawn Galvanized)			Approx. Weight Per Foot (lbs)	
Rope Diameter	I.P.S. F.C.	I.P.S. IWRC	E.I.P.S. IWRC	F.C.	IWRC
1/4"	2.74	2.94	3.4	0.105	0.116
5/16"	4.26	4.58	5.27	0.164	0.18
3/8"	6.1	6.56	7.55	0.236	0.26
7/16"	8.27	8.89	10.2	0.32	0.35
1/2"	10.7	11.5	13.3	0.42	0.46
9/16"	13.5	14.5	16.8	0.53	0.59
5/8"	16.7	17.9	20.6	0.66	0.72
3/4"	23.8	25.6	29.4	0.95	1.04
7/8"	32.2	34.6	39.8	1.29	1.42
1"	41.8	44.9	51.7	1.68	1.85
1-1/8"	52.6	56.5	65	2.13	2.34
1-1/4"	64.6	69.4	79.9	2.63	2.89
1-3/8"	77.7	83.5	96	3.18	3.5
1-1/2"	92	98.9	114	3.78	4.16
1-5/8"	107	115	132	4.44	4.88
1-3/4"	124	133	153	5.15	5.67
1-7/8"	141	152	174	5.91	6.5
2"	160	172	198	6.72	7.39